

Rubber Coated Metal Materials

金属橡胶复合材料

GN3825-SPCC

产品说明

该材料为新型密封材料，通过特定的生产工艺在金属基材表面均匀涂覆橡胶层；该材料具有良好的耐热、耐久性能，并且具有极低的压强永久变形率。与传统的非金属密封材料相比，该材料具有相对较长的使用寿命，因此，通常应用在压力更大、温度更高、密封要求更苛刻的使用环境中。

物理性能

项目	指标	
橡胶种类	丁腈橡胶	
金属基材	SPCC	
外观	亚光半黑色	
总厚度(MM)	0.38 ± 0.02	
基材厚度(MM)	0.25 ± 0.01	
橡胶厚度(MM)	0.065 ± 0.005 (单面)	
最高使用温度	≤	150℃
橡胶附着力	100%无脱落	
金属基材硬度(HV)	140-160	
浸渍IRM903油后性能 149 ± 2℃, 5h	增重率/ %	≤ 10
	增厚率/ %	≤ 8
浸渍ASTM燃油B后性能 21 ~ 30℃, 5h	增重率/ %	≤ 10
	增厚率/ %	≤ 8

Description

GN3825-SPCC is a new kind of sealing material that was produced from special procession of coating rubber overlaid evenly on the surface of metal core. Provide excellent performance of high-temperature resistance and durability. It has a relatively long shelf life than other traditional non-metallic sealing materials. Therefore, It was generally used in harsh environmental condition of extra pressure and ultra-temperature sealing requirement.

Technical Specifications

Property	Specification	
Rubber type	NBR	
Metal Core	SPCC	
Appearance	Semi-luster black	
Total thickness (MM)	0.38 ± 0.02	
Metal core thickness (MM)	0.25 ± 0.01	
Rubber coating thickness (MM)	0.065 ± 0.005 (Single side)	
Max. Operation Temp.	≤	150℃
Rubber Adhesives	100% no precipitation	
Metal Core Hardness Value(HV)	140-160	
Fluid Resistance (at ASTM IRM Oil #3, 149 ± 2℃, 5h)	Weight Change / %	≤ 10
	Thickness Change / %	≤ 8
Fluid Resistance (at ASTM fuel B, 21-30 °C, 5h)	Weight Change / %	≤ 10
	Thickness Change / %	≤ 8

www.teamful.net

天府密封科技

TEAMFUL SEALING TECHNOLOGY

总公司:

成都天府垫片科技有限公司
地址: 中国·四川省成都市双流县西南
航空港经济技术开发区双华路三段123号
电话: 86-028- 85875538
传真: 86-028- 85651433
邮件: sales@teamful.net

出口部:

电话: 86-028- 85875509
传真: 86-028- 85651433
邮件: qul@teamful.net

广东分公司

江门天府密封科技有限公司
地址: 中国·广东省江门市新会区大泽
镇创利来工业基地泽棠路
电话: 86-0750-6805518
传真: 86-0750-6805519
邮件: sales@teamfulgd.net

Teamful Headquarters

Chengdu Teamful Gasket Technology
Co.,Ltd.
ADD: No.123, Shuanghua Road Section 3,
the Southwest Airport Economic
Development Zone, Shuangliu, Chengdu,
P.R. China
Tel: 86-028- 85875538
Fax: 86-028- 85651433
Email: sales@teamful.net

Foreign Trade Dept.

电话: 86-028- 85875509
传真: 86-028- 85651433
邮件: qul@teamful.net

Guangdong Teamful Branch

JiangMen Teamful Sealing Technology
Co.,Ltd.
ADD: Zetang Road, Chuanglilai Industrial
Zone, Daze Town, Xinhui District, Jiangmen
City, Guangdong, P.R.China
TEL: 86-0750-6805518
FAX: 86-0750-6805519
Email: sales@teamfulgd.net

teamful
sealing